

Technical Data



SPECS

FEATURES

Dental Model White polymer has been formulated to create detailed, high resolution dental models on the LC Magna printer range. The resin has been developed in conjunction with Dental Technologists to ensure an optimal colour, feel, and working characteristics. Ideal for Orthodontic, study and working models. The prints show minimal shrinkage with a tolerance of 50µm max deviation on a full arch. Printed dental parts exhibit extremely high tensile properties and hardness, allowing for their use as a working or a vacuum forming model. Dental model resin will provide excellent print performance on the LC Precision printer range, allowing you to print crisp and clean dental models.

PROCESSING INSTRUCTIONS

Follow the procedures laid out in your 3D Liquid Crystal user manual. Polymer should be poured into the tray away from direct sunlight. Polymer can be reused but should be poured through a filter to remove solid lumps. Keep hood on at all times. Liquid polymer is soluble in water and soap. Object should be post cured under UV in 60°C warm water to obtain the appropriate tensile properties and give a great surface finish.

IDEAL APPLICATIONS

- Orthodontic moulds
- Die models
- Study Models

DATA

Viscosity (At 25°C Brookfield spindle 3)	900 cPs
Hardness ASTM D2240 (After post exposure)	90 Shore D
Tensile strength ASTM D638 (After post exposure Postcured 120 mins UV and heat 60°C water)	63 MPa
Elongation at break ASTM D638 (Postcured 120 mins UV and heat 60°C water)	4.3%
Storage	10\pm50°C
Density	1.09 g/cm ³

AVAILABLE COLOURS

White

Available in 5kg bottles.